

Intrinsic and Extrinsic Coloration of Maxillofacial Prosthesis: A Review Article

Shwetali Powar¹, Abhijit Deshpande², Sampath Kumar N.³,
Virsen Patil⁴, Snehal Shende⁵, S M Karthik⁶

How to cite this article:

Shwetali Powar, Abhijit Deshpande, Sampath Kumar N. *et al.* Intrinsic and Extrinsic Coloration of Maxillofacial Prosthesis: A Review Article. *Ind J Dent Educ.* 2024;17(4):183-186.

Abstract

Maxillofacial deformities may be congenital, resulting from malformations or developmental disturbances, or acquired, caused by conditions such as necrotizing diseases, oncological surgeries, or trauma. Often, surgical reconstruction is not feasible due to factors like the defect's size, location, or the patient's medical condition, making prosthetic rehabilitation essential. The success of such rehabilitation heavily relies on the physical and mechanical properties of the materials used. Contemporary materials include acrylic resins, acrylic copolymers, vinyl polymers, polyurethane elastomers, and silicone elastomers. Over the years, researchers have sought materials that replicate natural tissues in appearance and properties. This article discusses the historical evolution, emerging trends, and future directions in materials used for maxillofacial defect rehabilitation.

Keywords: Maxillofacial defect, Prosthetic materials, Rehabilitation, Silicone.

Key Message: Maxillofacial prostheses serve as a critical tool for individuals with facial defects resulting from congenital anomalies, trauma, or medical interventions. These prostheses aim to restore form, function, and aesthetics, significantly enhancing the patient's quality of life. Silicone elastomers, introduced in the 1960s, have proven to be among the most effective materials, offering durability, biocompatibility, and a lifelike appearance.

INTRODUCTION

Maxillofacial prostheses are invaluable in rehabilitating facial defects caused by congenital conditions, trauma, or surgical procedures. These prostheses not only restore aesthetics but also improve the functional and psychological well-being of patients. Introduced in 1960 by Barnhart, silicone elastomers have emerged

as the material of choice due to their biocompatibility, elasticity, and life-like appearance. The success of a maxillofacial prosthesis, however, largely depends on shade matching, a process influenced by the subjective perception of color. This review provides a comprehensive overview of the materials, techniques, and advancements that underpin successful maxillofacial prosthesis fabrication, with an emphasis on coloration methods.

Author's Affiliation: ¹P.G Student, ²Professor & HOD, ³⁻⁵Reader, ⁶Associate Professor, Department of Prosthodontics and Crown and Bridge, Tatyasaheb Kore Dental College and Research Centre, Nave Pargaon, Maharashtra 416113, India.

Corresponding Author: Shwetali Powar, P.G Student, Department of Prosthodontics and Crown and Bridge, Tatyasaheb Kore Dental College and Research Centre, Nave Pargaon, Maharashtra 416113, India.

E-mail: shwetaliPowar79@gmail.com

Received on: 21.10.2024

Accepted on: 14.12.2024



This work is licensed under a Creative Commons
Attribution-NonCommercial-ShareAlike 4.0.

Historical Overview of Maxillofacial Coloration Materials

The study of color stability in maxillofacial materials has been an area of interest since the late 1970s. Early research by Craig *et al.* (1978) noted no significant changes in luminous reflectance in polyurethane and silicone materials with aging.¹³ Haug *et al.*¹⁴ later highlighted color changes due to weathering in various elastomer-colorant combinations. Kiat Amnuay *et al.* (2009) demonstrated that opacifiers such as titanium white provided significant protection against color changes, while yellow silicone pigments exhibited pronounced instability.¹⁵ Subsequent studies, including those by Pesqueira *et al.* (2011), showed that ceramic pigments offered superior color stability compared to makeup pigments, particularly under conditions involving soap and effervescent cleaners.¹⁶ Bangera and Guttal (2014) explored the use of nanotechnology, finding that Zn nano-oxides offered better UV protection at lower concentrations compared to Ti nano-oxides.¹⁷ Bishal *et al.* (2019) further demonstrated the efficacy of TiO₂ nanocoatings in reducing color degradation of silicone elastomers under artificial aging.¹⁸

Concept of Coloration in Maxillofacial Prostheses

The success of maxillofacial prostheses depends heavily on the accurate replication of natural tissue colors. Chromism, a reversible color-changing process, plays a pivotal role in coloration. Researchers recommend selecting a base shade slightly lighter than the lightest skin tone of the patient to account for color darkening during pigment addition. The human skin's color results from light being reflected, refracted, and scattered. Coloration techniques are categorized into three types:

1. **Intrinsic Coloration:** Pigments are incorporated into the bulk material, forming the base color.
2. **Extrinsic Coloration:** Pigments are applied to the prosthetic surface for detailed finishing.
3. **Combination Techniques:** Integrating both methods for optimal results.

Lontz *et al.*¹⁹ described the physiological details of human skin coloration, highlighting arterial red, venous red-purple, carotenoid yellow, melanoid brown, and opaque cellular lipids. Johnston *et al.* applied the Kubelka-Munk reflectance theory to establish translucency parameters, enhancing the understanding of color matching.²⁰

Intrinsic Coloration Techniques

Intrinsic coloration involves incorporating pigments directly into the silicone base. Lemon *et al.*⁶ evaluated the efficacy of broad-spectrum UV light absorbers in maintaining the color stability of pigmented elastomers under artificial and natural weathering conditions. Their findings revealed perceptible color changes under varying radiant energy exposures. Aging, particularly temperature fluctuations, emerged as a significant factor influencing color stability.²¹

Extrinsic Coloration Techniques

Extrinsic coloration uses silicone adhesives thinned with solvents like xylene to achieve a liquid consistency. These adhesives act as a medium for applying pigments to the prosthesis surface. Adjustments can be made by reapplying pigments or removing excess with chloroform.²¹ Schaafis introduced tattooing as a coloring method, where fine needles deposit pigments beneath the prosthesis surface, enabling detailed characterizations.²²

Techniques of Coloration

Accurate coloration requires meticulous steps:

1. **Lighting Considerations:** Full-spectrum, color-corrected lighting minimizes metamerism. Shade matching is best performed under daylight, fluorescent, and incandescent lighting.
2. **Base Color Identification:** Pigments are mixed to achieve the desired base color. For Asian skin tones, white pigments are mixed with brown, umber, and sienna. Verification methods include photographs and preconstructed tissue shade guides.
3. **Pigment Placement in Molds:** Pigments are strategically loaded into molds, ensuring proper placement for accurate skin tone replication.

Currently Available Materials

Selection of prosthetic materials depends on their functional and aesthetic properties:

1. **Acrylic Resin:** Widely used for facial defects with minimal tissue movement.²³
2. **Acrylic Copolymers:** Flexible but limited by poor durability and edge strength.²⁴
3. **Polyvinyl Chloride:** Adaptable to intrinsic and extrinsic coloring but exhibits poor tear strength and color stability.^{25,26}

4. Silicone Elastomers: Introduced in 1946, these materials gained popularity due to their thermal stability and versatility. Heat vulcanized (HTV) and room temperature vulcanized (RTV) silicones are commonly used.^{9,27-30}

Recent advances include silicone block copolymers, polyphosphazenes, and foaming silicones. These materials address issues such as tear strength, elasticity, and bacterial resistance.^{31,32}

Effects of Various Conditions on Color Stability:

1. Human Conditions: Body secretions like sebum and perspiration can cause color changes, particularly under artificial daylight exposure.^{33,34}
2. Fabrication Procedures: Mechanical mixing under vacuum conditions reduces porosity and enhances color consistency compared to manual mixing.³⁵

CONCLUSION

The integration of digital dentistry and CAD-CAM technology has transformed the fabrication of realistic maxillofacial prostheses. Understanding the properties of various materials is essential to achieving optimal outcomes. Future research should focus on developing color-stable agents and standardized methods for shade matching. Advances in silicone-based materials have significantly benefited prosthodontists, while human factors and patient adaptation remain critical to the success of maxillofacial prostheses. This article provides a comprehensive overview of coloration methods and their role in the fabrication of maxillofacial prostheses.

Acknowledgement: NIL

Conflict of Interest: NIL

REFERENCES

1. Sethi T, Matani J, Kheur M, Jambhekar S. Pigments Used for Maxillofacial Prosthetics and A Step by Step Protocol for their Application.
2. dos Santos DM, Goiato MC, Moreno A, Pesqueira AA, Haddad MF. Influence of pigments and opacifiers on color stability of an artificially aged facial silicone. *J Prosthodont* 2011; 20:205-8.
3. Barnhart GW. A new material and technique in the art of somato-prosthesis. *J Dent Res* 1960; 39:836-44.
4. Cantor R, Webber R, Straud L, Ryge G. Methods for evaluating prosthetic facial materials. *J Prosthet Dent*. 1969; 21: 324-332.
5. Chen MS, Udagama A, Drane JB. Evaluation of facial prostheses for head and neck cancer patients. *J Prosthet Dent* 1981; 46: 538-554.
6. Lemon JC, Chambers MS, Jacobsen ML, et al: Color stability of facial prostheses. *J Prosthet Dent* 1995; 74: 613-618.
7. Raghuvanshi S, Chand P, Singh SV, Aggarwal H, Arya D. Nonimplant, nonadhesive overlay approach to retain a partial auricular prosthesis. *J Prosthodont*. 2019; 28(2):e826-9.
8. Beatty MW, Mahanna GK, Dick K, Jia W. Color changes in dry-pigmented maxillofacial elastomer resulting from ultraviolet light exposure. *J Prosthet Dent* 1995; 74:493-8.
9. Polyzois GL. Color stability of facial silicone prosthetic polymers after outdoor weathering. *J Prosthet Dent* 1999; 82:447-50.
10. Feldman D. Polymer weathering: Photo-oxidation. *J Polym Environ* 2002; 10:163-73.
11. Kantola R, Lassila LV, Tolvanen M, Valittu PK. Color stability of thermochromic pigment in maxillofacial silicone. *J Adv Prosthodont* 2013; 5:75-83.
12. Gupta P, Deshpande S, Radke U, Ughade S, Sethuraman R. The color stability of maxillofacial silicones: A systematic review and meta analysis. *J Indian Prosthodont Soc*. 2021; 21(2):138.
13. Craig RG, Koran A, Yu R, Spencer J. Color stability of elastomers for maxillofacial appliances. *J Dent Res* 1978;57:866-71.
14. Haug SP, Andres CJ, Moore BK. Color stability and colorant effect on maxillofacial elastomers. Part III: Weathering effect on color. *J Prosthet Dent* 1999; 81:431-8.
15. Kiat-Amnuay S, Lemon JC, Powers JM. Effect of opacifiers on color stability of pigmented maxillofacial silicone A-2186 subjected to artificial aging. *J Prosthodont* 2002; 11:109-16.
16. Pesqueira AA, Goiato MC, dos Santos DM, Haddad MF, Ribeiro Pdo P, Coelho Sinhoret MA, et al. Effect of disinfection and accelerated aging on color stability of colorless and pigmented facial silicone. *J Prosthodont* 2011; 20:305-9.
17. Bangera BS, Guttal SS. Evaluation of varying concentrations of nano-oxides as ultraviolet protective agents when incorporated in maxillofacial silicones: An in vitro study. *J Prosthet Dent* 2014; 112:1567-72.
18. Bishal AK, Wee AG, Barão VAR, Yuan JC, Landers R, Sukotjo C, et al. Color stability of maxillofacial prosthetic silicone functionalized with oxide

- nanocoating. *J Prosthet Dent* 2019; 121:538-43.
19. Lontz JF. State of the art material used for maxillofacial prosthetic reconstruction. *Dent Clin North Am* 1990; 34:307-25.
 20. Johnston, WM, Ma, T, Kienle, BH. Translucency parameter of colorants for maxillofacial prostheses. *Int J Prosthodont* 1995; 8:79-86.
 21. Takamata T, Moore BK, Chalian VA. Evaluation of color changes of silicone maxillofacial materials after exposure to sunlight. *Dent Mater J* 1989; 8:260-70.
 22. Shaarf N. Maxillofacial prosthetics and the head and neck cancer patient. Supplement: American Cancer Society National Conference on Advances in Cancer. 1984; 54(2):2682-2690.
 23. Coelho M, Alues Pesqueira A, Micheline Dos Santos D, Fiuza de Carvalho Dekon S. Influence of investment, disinfection and storage on the microhardness of ocular resins. *Journal of Prosthodontics* 2008;2(18): 32-35.
 24. Ring ME. The history of maxillofacial prosthetics. *Journal of Plast Reconstr Surg* 1991;87(1):174-184.
 25. Chalian VA, Philips RW. Materials in maxillofacial prosthetics. *Journal of Biomedical Materials Research Symposium* 1974;5(2):349-63.
 26. Dorsey J, Zorach J, Glazer, Tabacco MJ, Linebaugh MG. Evaluation of polymeric material for maxillofacial prosthetics. *J Prosthet Dent* 1977;38(3):319-26.
 27. Mohammad SA, Wee AG, Rumsey DJ, Schricker SR. Maxillofacial materials reinforced with various concentrations of polyhedral silsesquioxanes. *J Dent Biomech* 2010;1(1):821-832.
 28. Deba K, Yunus N, Kumar V, Ahmad N. Oral and maxillofacial prosthesis-II materialistic approach. *Heal Talk* 2012;4(6):18-20.
 29. Mitra A, Choudhary S, Garg H, Jagadeesh HG. Maxillofacial prosthetic materials-an inclination towards silicones. *J Clin Diag Res* 2014;8(12):8-13.
 30. Bellamy K, Limbert G, Waters MG, Middleton J. An elastomeric material for facial prostheses: synthesis, experimental and numerical testing aspects. *J Biomaterials* 2003;24:506-16.
 31. Mahajan H, Gupta K. Maxillofacial prosthetic materials: A literature review. *J Orofac Res* 2012;2(2):87-90.
 32. Catapano G, Verkerke GJ. Handbook of Research on Biomedical Engineering Education and Advanced Bioengineering Learning: Interdisciplinary Concepts. 2012;(2):53-55.
 33. Hatamleh MM, Watts DC. Effect of extraoral aging conditions on color stability of maxillofacial silicone elastomer. *J Prosthodont* 2010;19:536-43.
 34. Hatamleh MM, Watts DC. Porosity and color of maxillofacial silicone elastomer. *J Prosthodont* 2011;20:60-6.
 35. Filié Haddad M, Coelho M, Micheline Dos Santos D, Moreno A, Filipe D, Almeida N, Alves Pesqueira A. Color stability of maxillofacial silicone with nanoparticle pigment and opacifier submitted to disinfection and artificial aging. *J Biomed Opt* 2011;16:095004.